

TECHNICAL INFORMATION

SEAM SLIPPAGE RESISTANCE (mm) EN ISO 13936/2:2004; Load Method (180 N) Seam Slippage (mm)	WARP 2	WEFT 2
ABRASION RESISTANCE (End point) EN ISO 12947-2:1998 and EN 14465:2003/A1:2006	31.000	
ABRASION RESISTANCE (Change of aspect) / EN ISO 12947/4:1998 and EN 14465:2003/A1:2006 (Annex A; 3.000 cycles) Color Degradation on grey scale (From 1 worst to 5 best)	4	
PILLING RESISTANCE / EN ISO 12945/2:2000; Modified Martindale Method: 2000 and 7000 cycles / Pilling index (From 1 worst to 5 best)	5	
ASSESSMENT OF IGNITABILITY EN 1021-1:2006 (cigarette test) EN 1021-2:2006 (match test)	-	
LIGHTFASTNESS TO WEATHER / EN ISO 105-B04 (1000 hours) Color degradation on blue scale (From 1 worst to 8 best)	>6	
COLOR FASTNESS TO RUBBING / EN ISO 105-X12:2002. Degradation and loss of color on grey scale (From 1 worst to 5 best)	DRY 4-5	WET -
COLOR FASTNESS TO DOMESTIC (30°) EN ISO 105-C06:1997/AC:2009 – Color Degradation on grey scale (From 1 worst to 5 best)	-	
DIMENSIONAL CHANGE IN DOMESTIC WASHING AND DRYING (%) EN ISO 3759:2008 – EN ISO 6330:2000/A1:2009 – EN ISO 5077:2008	WARP -1%	WEFT -1%
TENSILE STRENGTH. BEFORE AND AFTER PUTREFACTION TEST EN ISO 13934-1:1999	A-1714/1956 D-1628/1968	
RESISTANCE TO PUTREFACTION AATCC 30:2004	-	
RESISTANCE TO SURFACE WETTING – SPRAY TEST EN 24920:1992	ISO 1	
RESISTANCE TO WATER PENETRATION – HYDROSTATIC PRESSURE TEST / EN 20811:1992	>2000mbar (20 metres)	
WATER FASTNESS / EN ISO 105-E01:1996 Color Degradation on grey scale (From 1 worst to 5 best)	4	
SWIMMING POOL CHLORINE FASTNESS / EN ISO 105-E03:1993 Color Degradation on grey scale (From 1 worst to 5 best)	4-5	
SEA WATER FASTNESS / EN ISO 105-E02:1996 Color Degradation on grey scale (From 1 worst to 5 best)	4-5	

SOILING AND CLEANABILITY / FORD FLTM BN 112-08:2005 (From 1 worst to 5 best)
*Red & black marking pen: 3 / Synthetic soil: 4-5 / Coffee: 4 / Colored pencil: 4-5 / Grease: 4
Red & blue ballpoint pen: 3-4 / Crayon: 4 / Orange juice: 5 / Ketchup : 4-5

ARTICLE: 1062 (WATERPROOF-OUTDOOR)
COMPOSITION: 44% PP 31% PES 18% CO 7% PU
WIDTH: 140 +4cm.
WEIGHT: 655 gr/mL +/- 5%

CARE INSTRUCTIONS



NOTES: PLEASE, ATTENTION WHEN WORKING WITH "VELCRO"

product info

collection 1062

composition 44% PP, 31% PES, 18% CO, 7% PU

width (± 4) 1.40 cm

weight ($\pm 5\%$) 655 g/ml

martindale 31.000

end use Upholstery – Cushion – Drapery