

TECHNICAL INFORMATION

ABRASION TEST EN ISO 12947-1,2	32.000 cycles (martindale)	Category A
PILLING TEST EN ISO 12945-2 (2.000T)	5	Category A
TENSILE STRENGTH EN ISO 13934-1	WARP 1422.9 N WEFT 469.6 N	Category A Category B
TEAR GROWTH RESISTANCE EN ISO 13937-3	WARP 80.4 N WEFT 45.4 N	Category A Category A
RESISTANCE TO SEAM SLIPPAGE EN ISO 13936-2	WARP 3.00 mm WEFT 3.00 mm	Category A Category A
FASTNESS TO RUBBING EN ISO 105-X12 DRY	Bright colors 5 Dark colors 5	Category A Category A
FASTNESS TO RUBBING EN ISO 105-X12 WET	Bright colors 4 Dark colors 4	Category A Category A
FASTNESS TO LIGHT EN ISO 105-B02	Bright colors 5 Dark colors 5	Category B Category B

TEST RESULTS WERE GATHERED FROM VARIOUS SAMPLES AND THEREFORE REPRESENT AVERAGE INDICATIVE VALUES.

FIRE PROTECTION	BS 5852 Part 0 Part DIN EN 1021-1,2	On request
SPOT PROTECTION		On request

ARTICLE: 204

WIDTH: 1,40cm ±2cm

THICKNESS: 1,1mm ±2%

WEIGHT m: DIN EN 12127, 434g ±5%

WEIGHT m²: DIN EN 12127, 310g ±5%

COMPOSITION SURFACE: 98% POLYESTER - 2% POLYAMIDE

COMPOSITION BASE: 100% POLYESTER

CARE INSTRUCTIONS



product info

collection 204

composition surface: 98% POLYESTER-2% POLYAMIDE
/ base: 100% POLYESTER

width (±2) 1.40 cm

weight (±5%) 310 g/m² / ± 434 g/m

martindale 32.000

end use Upholstery – Cushion – Drapery